

OPTIMIZATION OF PROCESS PARAMETERS OF NIMONIC(SU-263) USING TAGUCHI'S TECHNIQUE

Raju B.S, Professor, School of Mechanical Engineering, REVA University, Bangalore 560064,
Syed Mukthiyar Basha, Satyan Sangamesh, Tareeq Aziz, Chethan B.S, UG Student, Department of Mechanical Engineering, REVA University, Bangalore 560064 , India

Abstract

Nimonic/ SU (263) is a nickel base super alloy comprising of high temperature withstanding property, highly corrosion resistant and high strength because of its unique properties which is desired in various engineering and marine applications such as components of gas and jet engines, steam turbines and nuclear reactors. In our work an attempt is made to determine the optimal process parameters such as speed, feed, DOC on the response variable which are MRR, and Surface Roughness (Ra) during the turning operation on Nimonic/ SU (263). An L9 orthogonal array has been used with different levels of input parameters in order to minimize the experimental trials. The signal to noise ratio is determined w.r.t to the quality characteristics in order to determine the optimal parameters for the response variables. The Analysis of Variance is performed in order to predict the most significant parameter which affects the response variables and the end results are validated with Minitab software.

Keywords: Nimonic/ SU (263), Taguchi Technique, Orthogonal array, SN ratio, ANOVA.

Introduction

Super alloy, Nimonic series 718,600,700 is widely used in sophisticated applications due to its unique properties desired for the various engineering and marine applications. Due to its special characteristics, machining of super alloy is difficult and also costlier. Hence the present work mainly deals with the determination of optimal process parameters during the turning of Nimonic SU 263 using carbide tool insert as shown in the Fig.1. Nimonic SU 263 material is a nickel based super alloy. Taguchi method is one of the Design of experiment (DOE) tool for optimization of the process and also to identify the critical parameters with their optimal setting of it. Analysis of variance (ANOVA) is used to determine the effect of process parameters on the response variables. The input parameters such as speed, feed, degree of freedom on response variables tensile strength (Ts), material removal rate (MRR) and surface roughness (Ra) NIMONIC SU 263 is non-magnetic nickel-chromium-iron high temperature alloy having high strength, high corrosion resistance, hot and cold workability and free from stress corrosion. The high chromium content raises its oxidation resistance and the presence of high nickel content provides good corrosion resistance. The alloy shows very good levels of resistance to chloride stress-concentration cracking, ammonia. It has a good performance level at cryogenic temperatures. Since machining is a basically a finishing process with specified dimensions, stability, tolerance and surface finish, type of surface and its characteristics are very much important in manufacturing.

Carbide cutting tools are the oldest amongst the hard cutting tool materials in order to machine nickel based super alloys with the speed range of 30-80m/min. The 3D view of carbide tool insert is as shown in Fig.1 and general information on insert as listed in table 1.




Fig.1 Carbide tool insert & different types of tool insert.

Table 1- Tool insert specifications

Insert Style	VNMG
Material	Carbide(TiN/TiAlN)
Manufacture grade	IC907
Shape	Diamond
Length	16.6mm
Thickness	4.76mm
Application	Turning
Included Angle	35 degree(Right hand cut)
Full insert style code	VNMG160404

Factors affecting the quality of turning

The key mechanical input in material removal operation are speed, feed, depth of cut, tool insert, cutting force, coolant used etc. The choice of feed, speed and depth of cut is based on the customer objectives

Independent Variable

➤ Cutting Speed

In general, speed (V) is the primary cutting motion, which relates the velocity of the rotating work piece with respect to the stationary cutting tool. The cutting speed refers to the edge speed of the rotating work piece. It is generally given in unit of surface feet per minute (sfpm) or inches per minute (in/min), or meters per minute (m/min). For a given material there will be an optimum cutting speed for a certain set of machining conditions, and from this speed the spindle speed (RPM) can be calculated. Factors affecting the calculation of cutting speed are:

- The material being machined (steel, brass, tool steel, plastic, wood)
- The material the cutter is made from (Carbon steel, High speed steel (HSS), carbide and ceramics).
- The economic life of the cutter (the cost to regrind or purchase new, compared to the quantity of parts produced).

➤ Feed

Feed is the relative velocity at which the cutter is advanced along the work piece. Its vector is perpendicular to the vector of cutting speed. Feed rate units depend on the motion of the tool and work piece. When the work piece rotates (*e.g.*, in turning and boring), the units are almost always distance per spindle revolution (inches per revolution [in/rev] or millimeters per revolution [mm/rev]). When the work piece does not rotate (*e.g.*, in milling), the units are typically distance per time (inches per minute [in/min] or millimeters per minute [mm/min]), although distance per revolution or per cutter tooth are also sometimes used.

Feed rate is dependent on the:

- Type of tool
- Surface finish desired.
- Power available at the spindle.
- Rigidity of the machine and tooling setup (ability to withstand vibration or chatter).
- Strength of the work piece.
- Characteristics of the material being cut, chip flow depends on material type and feed rate. The ideal chip shape is small and breaks free early, carrying heat away from the tool and work.

➤ Depth of cut

Cutting speed and feed rate come together with depth of cut to determine the material removal rate, which is the volume of work piece material that can be removed per time unit. It is the distance that cutting tool penetrates into the work piece [3].

Response variables

➤ **Material removal rate**

The material removal rate of the work piece is the volume of the material removed per minute. It can be calculated using the following relation (1.1).

$$MRR = \frac{(W_i - W_f)}{D_w \times t} \dots\dots\dots(1.1)$$

MRR – Material Removal Rate (mm³/min)

W_i– Initial weight of work piece (gm)

W_f– Final weight of work piece (gm)

D_w– Density of the work piece (gm/mm³)

t - Period of trial (min)

➤ **Surface roughness**

Roughness is often a good predictor of the performance of a mechanical component, since irregularities in the surface may form nucleation sites for cracks or corrosion. Roughness is a measure of the texture of a surface. It is quantified by the vertical deviations of a real surface from its ideal form. If these deviations are large, the surface is rough; if small, the surface is smooth. Roughness is typically considered to be the high frequency, short wave length component of a measured surface. The parameter mostly used for general surface roughness is “Ra”. It measures average roughness by comparing all the peaks and valleys to the mean line, and then averaging them all over the entire cut-off length [3]. The surface roughness tester used for measuring the surface roughness is as shown in fig 2.



Fig2. Surface roughness tester (P.C – Mascot laboratories)

Method & Material

To achieve the required quality requirements in a specific situation, process parameters are often determined with the aid of building the parts of test specimen. A standard approach for experimental design is to use the full factorial method. However, a full factorial is acceptable only when a few factors are to be investigated. If more number of parameters are there, the full factorial method is time consuming and expensive. Hence the importance of Taguchi method for the design of experiments plays an important role. Taguchi methods of experimental design provide a simple, efficient and systematic approach called fractional factorial method for minimizing the number total experimental runs. The various parameter with level is as shown in table 1.

The steps of the proposed methodology are given below,

1. Identification of process parameters that influence on response variable with expertise knowledge and brainstorming.
2. Setting of levels for identified parameters to conduct experiments.
3. Selection of orthogonal array (OA) to design the experimental runs for main experiments by analyzing the interaction effect between the parameters.
4. Experimentation for the OA setting to find the values of response variables.

5. Prediction of optimal level for each parameter for the set objective with the response variable data using signal to noise (S/N) ratio.
6. Identification of critical parameters (most influencing) for the response variable with the percentage contribution of each parameter on the response variable using ANOVA techniques.

Table 1 Levels of various parameters

Parameter	Level 1	Level 2	Level 3
Speed in m/min	30	40	45
Feed in mm/rev	0.20	0.25	0.30
DOC in mm	0.6	0.7	0.8

Fabrication of test specimen

Machining of Nimonic (SU263) was carried out in CNC lathe and machining process involved cutting parameters such as cutting speed, feed and depth of cut. The measurements of material removal rate were made using observation of cutting time and further tested for surface roughness. The flow cart indicating the fabrication of test specimen is shown in the Fig.3. The raw material of nimonic su 263 is shown in image its dimensions are 20*160mm by using CNC turning machine and according to ASTM E8M standards and Taguchi L9 orthogonal array as shown in Fig.3(a & b).

Results and Discussions

The L9 orthogonal array with experimental results and calculated S/N ratios is shown in the table 2.

➤ **Effect of parameters on MRR**

S/N Ratio plot showing the variation of mean of SN Ratios and Cutting Speed with respect to different levels of parameters on MRR. It can be seen that the 3rd level of Vc that is 80m/min has the highest SN Ratio as shown in figure 4. Hence Vc =45m/min is more significant.




Fig 3 Flow chart indicating the fabrication of test specimen



Fig. 3. (a) raw material

(b) final component

Table 2 L9 orthogonal array with experimental results and calculated results for MRR Ra S/N ratio for MRR and Ra

Exp no.	Vc in mm/min	Feed in mm/rev	DOC inmm	MRR *10 ³ in mm ³ /min	a in micro meter	S/N ratio for MRR	S/N ratio for Ra
1	(1)30	(1)0.20	(1)0.6	0.194	0.336	-14.24	9.47
2	(1)30	(2)0.25	(2)0.7	0.242	0.208	-12.32	13.63
3	(1)30	(3)0.30	(3)0.8	0.299	0.217	-10.48	13.27
4	(2)40	(1)0.20	(2)0.7	0.258	0.314	-11.76	10.06
5	(2)40	(2)0.25	(3)0.8	0.328	0.239	-9.68	12.43
6	(2)40	(3)0.30	(1)0.6	0.389	0.220	-8.20	13.15
7	(3)45	(1)0.20	(3)0.8	0.294	0.210	-10.63	13.55
8	(3)45	(2)0.25	(1)0.6	0.382	0.315	-9.68	10.03
9	(3)45	(3)0.30	(2)0.7	0.464	0.268	-6.66	11.43




Fig 4. S/N ratio for speed v/s MRR levels

S/N Ratio plot showing mean of SN Ratio and DOC with respect to different levels of parameters on MRR. It can be seen that the 3rd Level of DOC that is 0.8mm has the highest SN Ratio as shown in figure 5. Hence DOC=0.8mm is more significant.




Fig 5: S/N ratio for DOC v/s MRR levels

S/N ratio plot showing mean of SN ratios and feed with respect to different levels of parameters on MRR. It can be seen that the 3 level of feed that is 0.2mm/rev has the highest SN Ratio as shown in figure 6. Hence feed=0.2mm/rev is more significant.




Fig:6: S/N ratio for feed v/s MRR levels

➤ **Effect of parameters on Surface Roughness**

S/N Ratio plot showing the variation of mean of SN Ratios and Cutting Speed with respect to different levels of parameters on Ra. It can be seen that the 3rd level of Vc that is 45m/min has the lowest SN Ratio as shown in figure 7. Hence Vc is 45m/min more significant.




Fig 7: S/N ratio for speed v/s Ra levels

S/N Ratio plot showing the variation of Mean of SN Ratios and Feed with respect to different levels of parameters on Ra. It can be seen that the 1st level of Feed that is 0.2mm/rev has the lowest SN Ratio as shown in figure 8. Hence feed is 0.2mm/rev is more significant.



Fig8: S/N ratio for feed v/s Ra levels

S/N Ratio plot showing mean of SN ratio and DOC with respect to different levels of parameters on Ra. It is observed that the 1st Level of DOC that is 0.6mm has the highest SN Ratio as shown in figure 9. Hence DOC is 0.6mm is more significant.




Fig 9: S/N ratio for DOC v/s Ra levels

Conclusions

In this project work, the material used is a super alloy Nimonic SU 263 which is costly material and possesses peculiar characteristics which makes it difficult to machine. Therefore, the selection of optimal parameters are important in order to minimize the higher unit cost per machined part and its service life. Analysis showed that in the turning of Nimonic SU 263 using conceptual S/N ratio approach. In this work, Taguchi method is used to provide the efficient and more effective design of experiment (DOE) technique to obtain simple, systematically and procedural methodology for the process optimization their interaction effects.

- **For MRR,**

- ❖ The parameters V_c , f , DOC influence much on the response factor MRR by S/N Ratio are, Speed (V_c)=45m/min; feed=0.3mm/rev; DOC =0.8mm
- ❖ The significance of each parameter is identified by ANOVA tool Speed (V_c)=48.52%; feed=45.43%; DOC =-1.2% of these three process parameters, Cutting speed (V_c) and Feed (f) has the major contribution on MRR

- **For Surface roughness**

- ❖ The parameters V_c , f , DOC influence much on the response factor R_a by S/N Ratio are, Speed (V_c)=45mm/min; feed=0.2mm/rev; DOC =0.6mm
- ❖ The significance of each parameter is identified by ANOVA tool Speed (V_c)=60.67% ; feed=7.2%; DOC =-7.21% of these three process parameters,

References

- [1] Wang, X., Da, Z. J., Balaji, A. K. and Jawahir, I.S. "Performance-Based Predictive Models Optimization Methods for Turning Operations and Applications-2007
- [2] Rao. RV. Pawar, P.J., Modelling and optimization of process parameters of wire electrical discharging machining, Proceedings of the Institution of Mechanical Engineers.-2009
- [3] Somashekar, K.P., Mathew, J. and Ramachandran, N. 'Multi-objective optimization of micro WEDM parameters using grey relational analysis with Taguchi method', Proceedings of the Institution of Mechanical Engineers, Part C: Journal of Mechanical Engineering Science-2011
- [4] Ilhan Asilturk, Harun Akkus. Determining the effect of cutting parameters on surface roughness in hard turning using the Taguchi method, Measurement 44 (2011).
- [5] Ezilarasan, C., Senthilkumar, V.S., Velayudham, A. and Palanikumar, K.,. Modeling and analysis of surface roughness on machining of Nimonic C-263 alloy by PVD coated carbide insert. Transactions of Nonferrous Metals Society of China.-2011
- [6] Ezilarasan, C., Senthilkumar, V.S. and Velayudham, A.,. Effect of machining parameters on surface integrity in machining nimonic C-263 super alloy using whisker-reinforced ceramic insert. Journal of Materials Engineering and Performances.-2013
- [7] Venkata Rao K, Murthy BSN, Rao NM, prediction of cutting tool wear, Surface roughness and Vibration of work piece in boring of AISI 316 steel with artificial neural networks. J. Measurement.-2014.
- [8] Goswami, A.; Kumar, J. Optimization in wire-cut EDM of Nimonic-80A using Taguchi's approach and utility concept. Eng. Sci. Technol. Int.J. 2014.
Sonawane, S.A.; Kulkarni, M.L. Optimization of machining parameters of WEDM for Nimonic-75 alloy using principal component analysis integrated with Taguchi method. J. King Sauduniv. Eng. Sci. 2018.